

Test results on the opposite page were provided by PPG Laboratories and were derived using the following methods.

Salt Spray - ASTM B117

Humidity - ASTM D714

Scribe - ASTM D1654

Gravelometer - ASTM D3170

Impact - ASTM D2794

Technical work flow for Godwin and Galion's standard paint application.

Wash and Degrease



Dry off



Automated shot blast




Partial cure and caulk



Zinc primer application



Topcoat application



Final cure and inspection



Before and after shot blasting

